

Product

Elastomeric membrane obtained by combining EPDM (Ethylene Propylene Diene Monomer) with oils and fillers followed by calendering and vulcanization. Provided with an extruded EPDM profile type 4511 for European grooves of 14 mm.


Application examples

- flood barrier under tresholds
- around curtain walls
- in steel and aluminium facades
- external facade insulation
- around frames/around windows



Colour: black

Thickness membrane: 0,75 mm / 1,00 mm / 1,30 mm



100-110-120-130-140-150-160-170-180-190-200-210-220-230-240-250-260-270-280-290-300-... - 1.420 mm

Length: 20 meter

The length might fluctuate \pm 5% due to the elasticity of the material.

Available versions

• strips with profile

Properties

- very good resistance to weather conditions, UV and aging
- √ very good long-term watertightness
- ✓ ready to install on window profile
- √ highly elastic and putrefaction resistant

Adhesive sealant NOVOPROOF® FA

A one component adhesive sealant made of synthetic rubber, which cures to a durable elastic rubber. Colour: black

Especially developed for bonding and sealing NOVOPROOF® FA EPDM to most common building materials such as aluminium (untreated, anodised, powder coated), mineral substrates (concrete, stone, clinker, plaster), PVC windows, steel (galvanised, powder coated), wood (pre-testing), overlaps between EPDM films. Aluminium sausages of 600 ml.

NOVOPROOF® FA EPDM WITH EXTRUDED PROFILE 14 MM – TYPE 4511



CE

Technical properties membrane

| Property membrane Value + unit | | | | |
|--|---|--|--|--|
| Density | value : unit | | | |
| o 0,75 mm o 1,00 mm o 1,30 mm | 0,94 kg/m ² 1,25 kg/m ² 1,625 kg/m ² | | | |
| Shore A hardness | 65° +/- 5 | | | |
| Temperature resistance | -30°C to +116°C | | | |
| Structure | single-layer solid rubber | | | |
| Elongation at break (EN 12311-1) o 0,75 mm | ≥ 400 % | | | |
| o 1,00 mm | ≥ 450 % | | | |
| o 1,30 mm | ≥ 450 % | | | |
| Tensile strength (EN 12311-1) | | | | |
| o 0,75 mm | ≥ 250 N/50 mm | | | |
| o 1,00 mm | ≥ 350 N/50 mm | | | |
| o 1,30 mm Tear resistance | ≥ 450 N/50 mm | | | |
| (EN 12310-1) | | | | |
| 0 0,75 mm | ≥ 80 N | | | |
| o 1,00 mm | ≥ 90 N | | | |
| o 1,30 mm | ≥ 90 N | | | |
| Fire class (EN ISO 11925-2/EN 13501-1) | Е | | | |
| Resistance to water vapour permeability | ≤ 0,1 m³/(m²/h/50 Pa) | | | |
| Water vapour diffusion resistance factor (μ) | 60.000 +/- 18.000 | | | |
| Certificates | ATG 2891 | | | |

Note

Always use a hard pressure roller for optimal adhesion. Two types are available: hard silicone rubber or steel.



NOVOPROOF® FA EPDM WITH EXTRUDED PROFILE 4511

Accessories

NOVOPROOF® Primer

Adhesion promoter for using the Kleber TA contact adhesive or the Kleber FA adhesive sealant on a porous, damp substrate or when applied at temperatures between +3°C and -10°C.

NOVOPROOF® Kleber TA

Contact adhesive based on synthetic rubber used for adhesion of the foil on all types of surfaces (wood, aluminium and stone).

NOVOPROOF® Cleaner

To clean the EPDM FA (if not clean enough) before bonding with the adhesive sealant FA or the contact adhesive Kleber TA.

| Property | Kleber TA | Kit FA | Primer |
|------------|-----------|------------|------------|
| Colour | black | black | black |
| Density | 0,85 Kg/l | 1,15 Kg/l | 0,835 Kg/l |
| Solids | 43,30 % | 79 % | 36,30 % |
| Flashpoint | -15°C | -8°C | -18°C |
| Viscosity | 400 mPa.s | 4500 mPa.s | 900 mPa.s |
| | +/- 100 | +/- 1000 | |
| Packaging | 4,7 Kg | 600 ml | 4,50 Kg |
| | | 12 per box | |
| Storage | 12 months | 12 months | 12 months |

Note

The information contained in this document is provided in good faith and is believed to be correct. However, we have no influence on the conditions in which these products are used or the methods by which they are used. Therefore, this information is not a substitute for tests which the customer must perform himself/herself in order to ensure that the products are safe, effective and achieve the intended purposes. Suggestions regarding the use of the product must not be used as grounds for infringement of any patent whatsoever. The only guarantee Castelein Sealants offers is that this product complies with the Castelein Sealants terms and conditions of sale in force at the time of shipment. Your only remedy in the event of a breach of this guarantee is the refund of the purchase price or the replacement of the product that does not comply with the guarantee.

Technical data of supplier: 05-2014

The producer reserves the right to make changes. 2022 02 03 $\,$