



Technical Data Sheet

DOWSIL™ 994 Ultra Fast Bonding Sealant

DOWSIL™ 994 Ultra Fast Bonding Sealant is a two-part neutral-cure silicone for structural glazing and automated assembly.

Features & Benefits

- Ultra-fast curing system allowing significant productivity improvements in continuous production processes, automated fabrications and specific bonding designs
- Meets European standard for structural glazing (ETAG 002)
- Ideal for bonding on UV-exposed surfaces due to excellent long term durability and UV resistance
- Excellent primer less adhesion to a wide range of substrates
- Specially designed for adhesion between glass and PVC, wood and aluminum window frames
- Excellent adhesion to a wide range of substrates including coated , enameled and reflective glasses, anodized and polyester paint coated aluminum and stainless steel
- High level of mechanical properties
- Stable viscosity for base and curing agent
- High level of structural capability
- High level of movement capability
- Odorless and non-corrosive cure
- Excellent stability through wide temperature range: -50°C to 150°C
- Fast application with easy-to-use 2-component pumping equipment
- Firm cycle time (e.g. Window and panel units can be moved along the line within a few minutes)
- Lot matching of base and curing agent not necessary
- European approval for structural glazing
- European Technical Approval ETA 18/0571 (color black)

Composition

- 2 part silicone sealant
- Neutral (moisture) cure

Applications

Ideal for continuous production processes, automated fabrications and specific bonding designs, e.g.:

- Structural glazing
- Windows and doors bonding
- Solar thermal bonding
- Internal partition wall bonding

Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Test ¹	Property	Unit	Result
Base: as supplied			
	Color and consistency		Viscous white paste
	Specific gravity	g/ml	1.34
	Viscosity (100 ^{s-1})	mPa.s	150,000
Curing agent: as supplied			
	Color and consistency		Viscous black paste
	Specific gravity	g/ml	1.03
	Viscosity (100 ^{s-1})	mPa.s	200,000
ASTM D93	Flash point - closed cup	°C	24
As mixed			
	Mixing ratio by weight (base/curing agent)		100:10 to 100:20 w / w (depending on the cure speed needed)
	Color and consistency		Black non-slump paste
ASTM D762	Specific gravity at 100:10	g/ml	1.31
ASTM D762	Specific gravity at 100:20	g/ml	1.29
	Working time (23°C 173°F, 50% R.H.)	minutes	3–10
	Tack-free time (23°C 173°F, 50% R.H.)	minutes	5–18
	Corrosiveness		Non-Corrosive
As cured: after 7 days at 23°C and 50% R.H.			
ISO 8339	Tensile strength	MPa	> 1.8
ASTM D624	Tear strength	kN/m	6.0
ISO 8339	Elongation at break	%	> 300
ASTM D2240	Durometer hardness, Shore A	points	45
	Sealant dynamic design load	Pa	140,000
	Sealant static design load	Pa	11,000
ASTM C711	Service temperature range	°C	-50 to +150

¹ASTM: American Society for Testing and Materials.

ISO: International Standardization Organization.

Description

DOWSIL™ 994 Ultra-Fast Bonding Sealant is a fast curing two-component, neutral silicone formulation specifically developed for structural glazing and for automated bonding applications where a fast and durable bond is required. DOWSIL™ 994 Bonding Sealant offers primerless superior adhesion on a wide variety of substrates (PVC, wood, Aluminum). Adhesion and durability performances on glass and various PVC substrates have been successfully tested according to ETAG 002. It supports demanding automated assembly processes for enhanced productivity. Neutral alkoxy; cures at room temperature giving off a small amount of alcohol.

UNRESTRICTED – May be shared with anyone

©™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

DOWSIL™ 994 Ultra Fast Bonding Sealant

© 2017–2019 The Dow Chemical Company. All rights reserved.

How To Use

DOWSIL™ 994 Ultra Fast Bonding Sealant offers unprimed adhesion to most coated and uncoated glasses as well most metal spacers. The sealant is compatible with DOWSIL™ neutral curing construction sealants such as DOWSIL™ 791 Silicone Weatherproofing Sealants, and DOWSIL™ neutral curing insulating glass sealants such as DOWSIL™ 3362 Insulating Glass Sealant and DOWSIL™ 3363 Insulating Glass Sealant, as well as most commonly used glazing components. It is important when selecting components for structural glazing and for a window bonding project that adhesion and compatibility tests are carried out, and found to be successful, before the production starts.

Mixing And Dispensing

To obtain the ultimate physical properties from DOWSIL™ 994 Ultra Fast Bonding Sealant it is recommended that the base and curing agent are thoroughly mixed using an airless mixing system found on most existing commercially available two-part silicone dispensing machines.

Suitable meter-mix equipment should be ideally equipped with gear pumps for base and catalyst, and a static mixer ensuring minimum level of variability in mixing ratio. DOWSIL™ 994 Ultra Fast Bonding Sealant cures at room temperature and develops chemical adhesion rapidly to several substrates. Mixing ratio and consequently cure speed of the bonding sealant can be adjusted according to the cycle times in production and the customer requirements. Use standard mixing ratio 100:10 up to 100:20 by weight for optimal properties. At this mixing ratio, the sealant typically exhibits a working time of 3–10 minutes. Small variations in mixing ratio can be tolerated, but these should not exceed 100:20 to 100:10 by weight to ensure minimum properties are obtained.

For each bonding project separately and depending on customer requirements, technical service will set up individual minimum and maximum tolerances in which material can be mixed.

Lot matching of DOWSIL™ 994 Base and DOWSIL™ 994 Curing Agent is not required. Before use it is recommended that the curing agent be stirred to ensure homogeneity of all components. DOWSIL™ 994 Curing Agent will react with atmospheric moisture and therefore should not be exposed to air for prolonged periods of time.

Cleaning

Clean all surfaces prior to application of sealant, hereby removing all foreign matter and contaminants such as grease, oil, dust, water, frost, surface dirt, old sealants, or glazing compounds and protective coatings. Metal, glass and plastic surfaces should be cleaned by solvent procedures. Solvent should be wiped on and off with clean, oil- and lint-free cloths. DOWSIL™ R-40 Cleaner is recommended for solvent cleaning of substrates. The ventilation time at room temperature should be at least 1 minute under factory conditions.

Priming

For each bonding or structural glazing project separately, it is essential that adhesion to all concerned surfaces should be tested before application. If adhesion requires priming, a primer such as DOWSIL™ 1200 OS Primer is in general recommended. When priming, the ventilation time at room temperature should be at least 1 minute under factory conditions. Project specific priming regulation needs to be discussed and approved.

How To Use (Cont.)

Masking And Tooling

Areas adjacent to joints may be masked to ensure a neat sealant line. Do not allow masking tape to touch clean surfaces to which the silicone sealant is to adhere. Tooling should be completed in one continuous stroke within 5 minutes after sealant application. Masking tape should be removed immediately after tooling.

Equipment Cleaning

When not being used it is recommended that the dispensing equipment be purged either with the base component, or flushed with a suitable solvent such as DOWSIL™ 3522 Concentrated Cleaning Solvent. If cured sealant has built up inside the equipment, flush the equipment for the appropriate time with DOWSIL™ 3522 Concentrated Cleaning Solvent, using a solvent recirculation system. This solvent dissolves cured silicone sealant and provides optimum cleaning performance.

Maintenance

No maintenance is needed. If sealant becomes damaged, replace damaged portion. DOWSIL™ 994 Sealant will adhere to cured silicone sealant which exhibits a clean knife-cut or abraded surface.

Bonding/Glazing

Although DOWSIL™ 994 Ultra Fast Bonding Sealant is specially designed to build up fast adhesion, it is important to respect cure time and curing conditions of the sealant during bonding/glazing and the consequent manufacturing steps. Once bonded/glazed, handling of the units/panels within production is possible already after a few minutes. However, the actual cure time depends on the mixing ratio. The adhesion builds up during the following hours. The final strength is reached after 24 hours. Consequently, units/panels can be installed after this period of time. A further requisite for a high quality bonding/glazing application consists in an appropriate joint dimension. Depending on parameters such as glass weight/panel weight, window/panel sizes but also temperatures etc., joint dimensions will vary between 2–4 mm by 8–10 mm. More specific recommendations about bonding are available in the quality manual for bonded windows and structural glazing.

Handling Precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT CONSUMER.DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

Usable Life And Storage

When stored at or below 25°C in the original unopened containers, DOWSIL™ 994 Black Curing Agent has a usable life of 12 months from the date of production.

When stored at or below 30°C in the original unopened containers, DOWSIL™ 994 Base has a usable life of 14 months from the date of production.

Packaging Information

DOWSIL™ 994 Base is available in 250 kg drums.

DOWSIL™ 994 Curing Agent is available in 25 kg pails.

Limitations

Because of the risk of incompatibility, DOWSIL™ 994 Sealant should not come into contact with, or be exposed to, sealants that liberate acetic acid.

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

Health And Environmental Information

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, consumer.dow.com or consult your local Dow representative.

consumer.dow.com

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

