



Membrane n° 22003
Classe : A-B-C

CE



ATG 3288

Product

Receptacle or made-to-measure, produced with an elastomer foil made of CS-EPDM Foil. All joints are hot-welded (450°C).

The preformed pieces can, depending on the type of substrate, be provided with a butyl adhesive strip of 1.50 mm x 20 mm.

These receptacles ensure a controlled and safe drainage of water.

Application examples

- flood barrier under thresholds
- controlled drainage
- under windows/frames

Colour : black

Available thicknesses

0,60 mm – 0,75 mm – 1,00 mm – 1,30 mm – 1,50 mm

Available versions

Receptacle or preformed piece based on the dimensions mentioned in the checklist.

The dimensions might fluctuate ± 5% due to the elasticity of the material.

Properties

- ✓ an extremely fast, simple and safe installation by 1 person
- ✓ very good resistance to weather conditions, UV and aging
- ✓ very good long-term watertightness
- ✓ highly elastic and putrefaction resistant
- ✓ recyclable
- ✓ solvent-free

Adhesives

CS-EPDM Mastic Bond FA

A 1-component synthetic rubber-based adhesive that cures to a durable elastic rubber. Colour: black.

CS-EPDM Foil Bond 00

A 1-component adhesive and sealant based on MS Hybrid technology that cures to a durable elastic rubber. Colour: black.

Both sealants are specially designed for bonding and sealing the CS-EPDM Foil to the most common building materials such as aluminium (untreated, anodized, powder-coated), mineral substrates (concrete, stone, clinker, plaster), PVC windows, steel (galvanized, powder-coated), wood (test beforehand), overlaps between EPDM foils. Aluminium sausages of 600ml.

Technical properties membrane

Property	Value + unit
Density (-5% / + 10%) (EN 1849-2)	
○ 0,60 mm	0,700 kg/m ²
○ 0,75 mm	0,875 kg/m ²
○ 1,00 mm	1,180 kg/m ²
○ 1,30 mm	1,575 kg/m ²
○ 1,50 mm	1,815 kg/m ²
Shore A hardness	65° +/- 5
Temperature resistance	-40°C to +120°C
Structure	Single layer solid rubber
Elongation at break (EN 12311-2B)	≥ 350%
Tensile strength (EN 12311-2B)	≥ 8,5 N/mm ²
Tear resistance (EN 12310-1)	
○ 0,60 mm	≥ 70 N
○ 0,75 mm	≥ 80 N
○ 1,00 mm	≥ 90 N
○ 1,30 mm	≥ 110 N
○ 1,50 mm	≥ 120 N
Fire class (EN ISO 11925-2/EN 13501-1)	E
Airtightness (EN 12114)	≤ 0,1m ³ /(m ² h) (50 Pa)
Water vapour diffusion resistance factor (μ) (EN 1931)	60.000 +/- 18.000
Certificates	ATG 3288

CS-EPDM FOIL RECEPTACLE

Notes

Thoroughly degrease the joinery with a universal cleaner type Dowsil™ R-40 and a soft, lint-free cloth.

The full width of the adhesive tape provided on the membrane (20 mm) must be used for adhesion to the substrate.

Due to the variety of substrates (product, structure, porosity, composition), it is necessary to test the product on the substrate before application, as the adhesive butyl tape present on the EPDM film may react differently.

Application of the CS-EPDM Foil Primer on porous substrates such as concrete is necessary.

Accessories

CS-EPDM Foil Primer

Adhesion improver for the use of contact adhesive CS-EPDM Contact Bond TA or bonding sealant CS-EPDM Mastic Bond FA on porous, damp substrates or in the case of use at temperatures between +5°C and -10°C.

CS-EPDM Contact Bond TA

Contact adhesive based on synthetic rubber used for bonding the membrane to all kinds of substrates (wood, aluminum and stone).

CS-EPDM Cleaner

To clean the CS-EPDM Foil (if not clean enough) before bonding with the CS-EPDM Mastic Bond FA or the contact adhesive CS-EPDM Contact Bond TA.

Properties: see technical data sheets of the products.

Note

The information contained in this document is provided in good faith and is believed to be correct. However, we have no influence on the conditions in which these products are used or the methods by which they are used. Therefore, this information is not a substitute for tests which the customer must perform himself/herself in order to ensure that the products are safe, effective and achieve the intended purposes. Suggestions regarding the use of the product must not be used as grounds for infringement of any patent whatsoever. The only guarantee Castelein Sealants offers is that this product complies with the Castelein Sealants terms and conditions of sale in force at the time of shipment. Your only remedy in the event of a breach of this guarantee is the refund of the purchase price or the replacement of the product that does not comply with the guarantee.

Technical data of supplier: 07/2024

The producer reserves the right to make changes. 2024 11 29